



**HSSCo8, MULTI FLUTE REGULAR LENGTH COARSE PITCH ROUGHING**

► This general purpose rougher is designed for high production metal removal in a wide range of work piece material. It is recommended for cutting steel grades and many non-ferrous materials. The end tooth of this tool has a center hole design for many accurate resharpenings between centers.



P.885, 890, 894

Unit : Inch

EDP No. 8% COBALT (M42)	Mill Diameter	Shank Diameter	Length of Cut	Overall Length	No. of Flute
60297	1/4	3/8	5/8	2-7/16	3
60301	5/16	3/8	3/4	2-1/2	3
60305	3/8	3/8	3/4	2-1/2	4
60312	7/16	3/8	1	2-11/16	4
60321	1/2	1/2	1-1/4	3-1/4	4
60328	9/16	1/2	1-3/8	3-3/8	4
60337	5/8	5/8	1-5/8	3-3/4	4
60348	11/16	5/8	1-5/8	3-3/4	4
60358	3/4	5/8	1-5/8	3-3/4	4
60359	3/4	3/4	1-5/8	3-3/4	4
60375	13/16	3/4	1-7/8	4-1/8	4
60391	7/8	3/4	1-7/8	4-1/8	5
60394	7/8	7/8	1-7/8	4-1/8	5
60409	15/16	7/8	1-7/8	4-1/8	5
60422	1	3/4	2	4-1/4	5
60426	1	1	2	4-1/2	5
60431	1-1/8	3/4	2	4-1/4	6
60435	1-1/8	1	2	4-1/2	6
60439	1-1/4	3/4	2	4-1/4	6
60445	1-1/4	1-1/4	2	4-1/2	6
60449	1-3/8	3/4	2	4-1/4	6
60457	1-1/2	3/4	2	4-1/4	6
60461	1-1/2	1-1/4	2	4-1/2	6
60467	1-3/4	3/4	2	4-1/4	6
60469	1-3/4	1-1/4	2	4-1/2	6
60475	2	3/4	2	4-1/4	6
60477	2	1-1/4	2	4-1/2	6
* 60480	2	2	2	5-3/4	8
* 60482	2	2	3	6-3/4	8
* 60484	2	2	4	7-3/4	8

\* Combination Shank

TECHNICAL DATA

Mill Dia. Tolerance (inch)	
up to 1	0~+.0030
over 1	0~+.0060


- The TiN coated, TiCN coated or TiAlN coated is available on your request.
- Coating Codes for Cobalt  
Uncoated EDP NO. + CN(TiN), CC(TiCN), CF(TiAlN F), CE(TiAlN E), CH(Hardslick)
- Coated Price Shown in Price List. Call for Availability.

◎ : Excellent ○ : Good

Carbon Steels	Alloy Steels	Prehardened Steels	Hardened Steels		High Hardened Steels	Copper	Graphite	Cast Iron	Aluminum	Stainless Steels	Titanium	Inconel
~HRc20	HRc20~30	HRc30~40	HRc40~45	HRc45~55	HRc55~70							
◎	◎	○				○			○			

**HSSCo8, MULTI FLUTE ROUGHING - SIDE CUTTING**

MATERIAL	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	HARDNESS	~HRc20		HRc20~HRc30		HRc30~HRc40				
STRENGTH	~ 500N/mm <sup>2</sup>		500~800N/mm <sup>2</sup>		800~1000N/mm <sup>2</sup>		1000~1300N/mm <sup>2</sup>			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	1800	3.1	1600	2.4	1200	2.2	800	1.2	4500	7.9
5/16	1400	4.1	1100	3.0	900	2.6	560	1.4	3100	9.1
3/8	1100	6.0	900	4.7	800	4.3	450	2.4	2500	13.8
1/2	900	7.1	800	5.5	630	4.3	400	2.8	2000	15.8
5/8	700	7.1	560	5.5	450	4.3	280	2.8	1600	17.7
11/16	630	7.1	500	5.5	400	4.3	250	2.8	1400	18.5
7/8	500	8.7	450	6.7	350	5.5	220	3.4	1100	18.5
1	450	8.7	400	6.7	310	5.5	180	3.4	1000	17.7
1-1/8	400	8.1	350	6.3	280	5.1	160	3.4	900	20.1
1-1/4	350	8.1	280	6.3	220	5.1	140	3.4	800	19.7
1-3/8	310	8.1	250	6.3	200	5.1	120	3.4	700	18.5
1-3/4	280	7.9	220	6.0	180	4.7	110	3.1	630	17.7
2	220	7.9	180	6.7	160	5.5	90	3.1	500	14.6




※ The Feed, in long &amp; extra long types, should be reduced by around 50%.

 RPM = rev./min.  
FEED = inch/min.

**HSSCo8, MULTI FLUTE BALL NOSE ROUGHING - SIDE CUTTING**

MATERIAL	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	HARDNESS	~HRc20		HRc20~HRc30		HRc30~HRc40				
STRENGTH	~ 500N/mm <sup>2</sup>		500~800N/mm <sup>2</sup>		800~1000N/mm <sup>2</sup>		1000~1300N/mm <sup>2</sup>			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
R5/32 × 5/16	1400	4.1	1100	3.0	900	2.6	560	1.4	3100	9.1
R3/16 × 3/8	1100	6.0	900	4.7	800	4.3	450	2.4	2500	9.8
R1/4 × 1/2	900	7.1	800	5.5	630	4.3	400	2.8	2000	15.8
R5/16 × 5/8	700	7.1	560	5.5	450	4.3	280	2.8	1600	17.7
R7/16 × 7/8	560	7.1	450	5.5	400	4.3	220	2.8	1200	19.7
R1/2 × 1	450	8.7	400	6.7	310	5.5	180	3.4	1000	17.7
R5/8 × 1-1/4	350	8.1	280	6.3	220	5.1	140	3.4	800	19.7
R7/8 × 1-3/4	280	7.9	220	6.0	180	4.7	110	3.1	630	17.7



※ The Feed, in long &amp; extra long types, should be reduced by around 50%.

 RPM = rev./min.  
FEED = inch/min.

 CBN  
END MILL

 i-Xmill  
END MILL

 X5070  
END MILLS

 4G MILLS  
END MILLS

 X-SPEED  
ROUGHER  
END MILLS

 X-POWER  
END MILLS

 JET-POWER  
END MILLS

 V7 Mill STEEL  
END MILLS

 V7 Mill INOX  
END MILLS

 ALU-POWER  
END MILLS

 D-POWER  
END MILLS

 STANDARD  
CARBIDE  
END MILLS

 TANK-POWER  
END MILLS

 STANDARD  
COBALT  
& HSS  
END MILLS

 TECHNICAL  
DATA

**HSSCo8, MULTI FLUTE ROUGHING TiN-COATED - SIDE CUTTING**

CBN END MILL

i-Xmill END MILL

X5070 END MILLS

4G MILLS END MILLS

X-SPEED ROUGHER END MILLS

X-POWER END MILLS

JET-POWER END MILLS

V7 Mill STEEL END MILLS

V7 Mill INOX END MILLS

ALU-POWER END MILLS

D-POWER END MILLS


STANDARD CARBIDE END MILLS

TANK-POWER END MILLS

STANDARD COBALT & HSS END MILLS

TECHNICAL DATA

MATERIAL	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~ 500N/mm <sup>2</sup>		500~800N/mm <sup>2</sup>		800~1000N/mm <sup>2</sup>		1000~1300N/mm <sup>2</sup>			
HARDNESS			~HRc20		HRc20~HRc30		HRc30~HRc40			
STRENGTH			500~800N/mm <sup>2</sup>		800~1000N/mm <sup>2</sup>		1000~1300N/mm <sup>2</sup>			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	2160	3.7	1920	2.9	1440	2.6	960	1.4	5400	9.5
5/16	1680	4.9	1320	3.6	1080	3.1	672	1.7	3720	10.9
3/8	1320	7.2	1080	5.6	960	5.2	540	2.9	3000	16.6
1/2	1080	8.5	960	6.6	756	5.2	480	3.4	2400	19.0
5/8	840	8.5	672	6.6	540	5.2	336	3.4	1920	22.2
11/16	756	8.5	600	6.6	480	5.2	300	3.4	1680	22.2
7/8	600	10.4	540	8.0	420	6.6	264	4.1	1320	21.2
1	540	10.4	480	8.0	372	6.6	216	4.1	1200	21.2
1-1/8	480	9.7	420	7.6	336	6.1	192	4.1	1680	24.1
1-1/4	420	9.7	336	7.6	264	6.1	168	4.1	960	23.6
1-3/8	372	9.7	300	7.6	240	6.1	144	4.1	840	22.2
1-3/4	336	9.5	264	7.2	216	5.6	132	3.7	756	21.2
2	264	9.5	216	8.0	192	6.6	108	3.7	600	17.5




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.  
FEED = inch/min.

**HSSCo8, MULTI FLUTE ROUGHING & FINISHING TiN-COATED - SIDE CUTTING**

MATERIAL	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~ 500N/mm <sup>2</sup>		500~800N/mm <sup>2</sup>		800~1000N/mm <sup>2</sup>		1000~1300N/mm <sup>2</sup>			
HARDNESS			~HRc20		HRc20~HRc30		HRc30~HRc40			
STRENGTH			500~800N/mm <sup>2</sup>		800~1000N/mm <sup>2</sup>		1000~1300N/mm <sup>2</sup>			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	2160	3.0	1920	2.4	1440	2.2	960	1.2	5400	7.6
5/16	1680	4.0	1320	2.9	1080	2.4	672	1.4	3720	8.8
3/8	1320	5.6	1080	4.4	960	4.2	540	2.4	3000	13.2
1/2	1080	6.8	960	5.2	756	4.2	480	2.6	2400	15.1
5/8	840	6.8	672	5.2	540	4.2	336	2.6	1920	17.6
11/16	756	6.8	600	5.2	480	4.2	300	2.6	1680	18.0
7/8	600	8.3	540	6.4	420	5.2	264	3.4	1320	18.0
1	540	8.3	480	6.4	372	5.2	216	3.4	1200	17.6
1-1/4	420	8.0	336	6.1	264	4.9	168	3.4	960	19.0
1-3/8	372	8.0	300	6.1	240	4.9	144	3.4	840	18.0
2	288	6.4	228	4.8	192	4.1	132	3.1	600	13.4



※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.  
FEED = inch/min.

**HSSCo8, MULTI FLUTE ROUGHING TiCN-COATED - SIDE CUTTING**

CBN END MILL

i-Xmill END MILL

X5070 END MILLS

4G MILLS END MILLS

X-SPEED ROUGHER END MILLS

X-POWER END MILLS

JET-POWER END MILLS

V7 Mill STEEL END MILLS

V7 Mill INOX END MILLS

ALU-POWER END MILLS

D-POWER END MILLS


STANDARD CARBIDE END MILLS

TANK-POWER END MILLS

STANDARD COBALT & HSS END MILLS

TECHNICAL DATA

MATERIAL	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~ 500N/mm <sup>2</sup>		500~800N/mm <sup>2</sup>		800~1000N/mm <sup>2</sup>		1000~1300N/mm <sup>2</sup>			
HARDNESS			~HRc20		HRc20~HRc30		HRc30~HRc40			
STRENGTH			500~800N/mm <sup>2</sup>		800~1000N/mm <sup>2</sup>		1000~1300N/mm <sup>2</sup>			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	2340	4.0	2080	3.1	1560	2.9	1040	1.6	5850	10.3
5/16	1820	5.3	1430	3.9	1170	3.4	728	1.8	4030	11.5
3/8	1430	7.8	1170	6.1	1040	5.6	585	3.1	3250	17.9
1/2	1170	9.2	1040	7.2	819	5.6	520	3.6	2600	20.5
5/8	910	9.2	728	7.2	585	5.6	364	3.6	2080	24.1
11/16	819	9.2	650	7.2	520	5.6	325	3.6	1820	24.1
7/8	650	11.3	585	8.7	455	7.2	286	4.4	1430	23.0
1	585	11.3	520	8.7	403	7.2	234	4.4	1300	23.0
1-1/8	520	10.5	455	8.2	364	6.6	208	4.4	1170	26.1
1-1/4	455	10.5	364	8.2	286	6.6	182	4.4	1040	25.6
1-3/8	403	10.5	325	8.2	260	6.6	156	4.4	910	24.1
1-3/4	364	10.3	286	7.8	234	6.1	143	4.0	819	23.0
2	286	10.3	234	8.7	208	7.2	117	4.0	650	19.0




※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.  
FEED = inch/min.

**HSSCo8, MULTI FLUTE ROUGHING & FINISHING TiCN-COATED - SIDE CUTTING**

MATERIAL	CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		CARBON STEELS ALLOY STEELS TOOL STEELS		ALUMINUM ALUMINUM ALLOYS	
	~ 500N/mm <sup>2</sup>		500~800N/mm <sup>2</sup>		800~1000N/mm <sup>2</sup>		1000~1300N/mm <sup>2</sup>			
HARDNESS			~HRc20		HRc20~HRc30		HRc30~HRc40			
STRENGTH			500~800N/mm <sup>2</sup>		800~1000N/mm <sup>2</sup>		1000~1300N/mm <sup>2</sup>			
DIAMETER	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED	RPM	FEED
1/4	2340	3.3	2080	2.6	1560	2.3	1040	1.3	5850	8.2
5/16	1820	4.4	1430	3.1	1170	2.6	728	1.6	4030	9.5
3/8	1430	6.1	1170	4.8	1040	4.6	585	2.6	3250	14.3
1/2	1170	7.4	1040	5.6	819	4.6	520	2.9	2600	16.4
5/8	910	7.4	728	5.6	585	4.6	364	2.9	2080	18.5
11/16	819	7.4	650	5.6	520	4.6	325	2.9	1820	19.5
7/8	650	9.0	585	6.9	455	5.6	286	3.6	1430	19.5
1	585	9.0	520	6.9	403	5.6	234	3.6	1300	18.5
1-1/4	455	8.7	384	6.6	286	5.3	182	3.6	1040	20.5
1-3/4	403	8.7	325	6.6	260	5.3	156	3.6	910	19.5
2	312	7.0	247	5.2	238	4.4	143	3.9	650	14.6



※ The Feed, in long & extra long types, should be reduced by around 50%.

RPM = rev./min.  
FEED = inch/min.